

AET Lézaud GmbH, Am Hottenwald 8, 66606 St. Wendel

+49 (0)6851/97394 0 +49 (0)6851/97394 44 ✉ industrie@lezaud.de 🌐 www.lezaud.de

Technical data sheet Status: 01.06.2021

profiles

LEZ-GOM TEX

Pos	Parameter	Value	Unit	Norm
	Elastomer base	SEBS		
	Geometry	Profile		
	Density	0,5	g/cm ³	ISO 2781
	Hardness	25 +/-5	Shore A	ISO 868
	Compression set	96 at -10°C (60 min); 24 h	%	BS 7412
	Compression set	81 at 23°C (60 min); 24 h	%	BS 7412
	Compression set	49 at 55°C (60 min); 14 days	%	BS 7412
	Temperature	-50 to +75	°C	
	Color	white		

Pos*	Compliant	Addition
	EG 1935/2004	
	EU 10/2011	

Pos* A= Outside; IN= Inside, S1= Side1,,S2= Side2

The values of these specifications come from regular controls of the compounds with the aid of norm samples and perform an average. They correspond to the actual state of the knowledge, the latest development of the sciences and our experience. They do not specify sure properties for the finals products. The indications in this data sheet are only a description of the typical properties and represent an aid and information for the user to give him some suggestions for his own application. But it remains in his responsibility to make sure with a specific trial that our product suits for his own purpose.

We strive to continuously improve our products. We reserve the right to modify and adjust the data sheet and our blends referring to the material properties. These will be documented with a new change status (date).