

AET Lézaud GmbH, Am Hottenwald 8, 66606 St. Wendel

☎ +49 (0)6851/97394 0 📠 +49 (0)6851/97394 44 ✉ [industrie@lezaud.de](mailto:industrie@lezaud.de) 🌐 [www.lezaud.de](http://www.lezaud.de)

Technical data sheet      Status: 01.06.2021

tubes

## LEZ-THERMOBLOND

Pos	Parameter	Value	Unit	Norm
	Elastomer base	SEBS		
	Geometry	Tube		
	Density	0,9	g/cm <sup>2</sup>	DIN 53479
	Hardness	40 +/-5	Shore A	ISO 868
	Tensile strength	5	MPa	ISO 527
	Elongation	800	%	ISO 527
	Temperature	-50 to +90	°C	
	Color	amber-colored		
Pos*	Compliant	Addition		
	FDA 21 CFR §177 2600			
	EG 1935/2004			
	EU 10/2011			

Pos\* A= Outside; I= Inside, S1= Side1, S2= Side2

The values of these specifications come from regular controls of the compounds with the aid of norm samples and perform an average. They correspond to the actual state of the knowledge, the latest development of the sciences and our experience. They do not specify sure properties for the finals products. The indications in this data sheet are only a description of the typical properties and represent an aid and information for the user to give him some suggestions for his own application. But it remains in his responsibility to make sure with a specific trial that our product suits for his own purpose.

We strive to continuously improve our products. We reserve the right to modify and adjust the data sheet and our blends referring to the material properties. These will be documented with a new change status (date).