

AET Lézaud GmbH, Am Hottenwald 8, 66606 St. Wendel

☎ +49 (0)6851/97394 0 📠 +49 (0)6851/97394 44 ✉ industrie@lezaud.de 🌐 www.lezaud.de

Technical data sheet Status: 01.06.2021

Accessories

LEZ-VITSEAL

Pos	Parameter	Value	Unit	Norm
	Elastomer base	FKM, copolymer, peroxid		
		Sealing Paste		
	Density	1,9 +/-0,03	g/cm³	DIN ISO 815 B
	Hardness	75	Shore A	DIN ISO 7619
	Tensile strength	>12	N/mm²	DIN 53504
	Elongation at break	>160	%	DIN 53504
	Compression set	20 at 175 °C; 24 h	%	DIN ISO 815 B
	Color	black		
	Temperature	-40 to +250	°C	

Pos* A= Outside; IN= Inside, S1= Side1; S2= Side2

The values of these specifications come from regular controls of the compounds with the aid of norm samples and perform an average. They correspond to the actual state of the knowledge, the latest development of the sciences and our experience. They do not specify sure properties for the final products. The indications in this data sheet are only a description of the typical properties and represent an aid and information for the user to give him some suggestions for his own application. But it remains in his responsibility to make sure with a specific trial that our product suits for his own purpose.

We strive to continuously improve our products. We reserve the right to modify and adjust the data sheet and our blends referring to the material properties. These will be documented with a new change status (date).