

AET Lézaud GmbH, Am Hottenwald 8, 66606 St. Wendel

☎ +49 (0)6851/97394 0 📠 +49 (0)6851/97394 44 ✉ [industrie@lezaud.de](mailto:industrie@lezaud.de) 🌐 [www.lezaud.de](http://www.lezaud.de)

Technical data sheet      Status: 05.10.2023

sheets, foils

## LEZ-VIT 65 FG

Pos	Parameter	Value	Unit	Norm
	Elastomer base	FKM		
	Geometry	sheet		
	Hardness	65 +/-5	Shore A	DIN ISO 7619
	Tensile strength	> 9	N/mm <sup>2</sup>	DIN 53405
	Elongation at break	> 180	%	DIN 53405
	Compression set	<=30 at 200°C; 22 h	%	DIN ISO 815 B
	Color	green		
	electr. contact resistance at rt	10E7	Ohm	
Pos*	Compliant	Addition		
	FDA 21 CFR §177 2600			

Pos\* A= Outside; IN= Inside, S1= Side1;;S2= Side2

The values of these specifications come from regular controls of the compounds with the aid of norm samples and perform an average. They correspond to the actual state of the knowledge, the latest development of the sciences and our experience. They do not specify sure properties for the finals products. The indications in this data sheet are only a description of the typical properties and represent an aid and information for the user to give him some suggestions for his own application. But it remains in his responsibility to make sure with a specific trial that our product suits for his own purpose.

We strive to continuously improve our products. We reserve the right to modify and adjust the data sheet and our blends referring to the material properties. These will be documented with a new change status (date).